

Technical Data Product Information

CS 4100Q
Decorative Quartz Epoxy Flooring System

Description

CS 4100Q is a 1/8" 100% solids epoxy resin decorative colored quartz flooring system engineered to provide good wear qualities along with a decorative finish. Suitable for light duty areas that focus attention to aesthetics. Can be used in conjunction with CornerStone membranes to provide a complete waterproofing system.

Colors

Color should be selected from the CornerStone Quartz Color Chart for this product available online at www.cornerstoneflooring.com. Special colors available at an additional charge.

Limitations

- Where floor temperatures are below 65°F or above 80°F during application contact CornerStone's Technical Department.
- For on-grade installations that do not have a vapor barrier under the slab or in areas where high water table or hydrostatic pressure conditions are present.
- Areas subject to strong chemicals.
- On a structurally unsound substrate.
- Avoid exposure from sunlight or other high UV output lighting.

Installation Procedures

SUBSTRATE PREPARATION

Prepare substrate by shot blasting, scarification or other mechanical means until an appropriate profile is evident. Remove all excess dust, curing agents and contaminants. Surface must be free of oils, water and chemicals.

ADVANTAGES	APPLICATIONS
• Good Wear Qualities	• Laboratories
• Chemical Resistant	• Corridors & Auditoriums
• Skid Resistant	• Locker Rooms & Restrooms
• Aesthetically Pleasing	• Cafeterias & Break Rooms
• Colored Quartz	• Light Traffic Areas

CS 4100Q APPLICATION

1. Apply specified polymer primer.
2. Broadcast aggregate.
3. Apply CS 2160 grout coat with a squeegee. Immediately back roll with 1/4" nap roller.
4. Broadcast aggregate.
5. Sweep off excess aggregate.
6. Sand surface.
7. Sweep floor to remove aggregate.
8. Apply CS 2160 topcoat with a squeegee. Immediately back roll with 1/4" nap roller.

Additional Topcoat Options: CS 2300CR, CS 2600SF

APPLICATION	COMPONENTS	MIX RATIO
Primer	As Specified	Per Label
Aggregate	As Specified	Per Label
Grout Coat	CS 2160A/2160B	Per Label
Color Quartz	As Specified	Per Label
Topcoat	CS 2160A/2160B	Per Label

Chemical Resistance

Refer to the Chemical Resistance Guide for specific chemical resistance information or contact CornerStone's Technical Department.

Cure Schedule

At an ambient temperature above 70°F, CS 4100Q can support foot traffic within 16 hours, full usage after 24 hours.

Maintenance

Regular cleaning and maintenance will prolong the life of all polymer flooring systems and enhance their appearance.


Safety

Avoid personal exposure. Refer to MSDS for additional safety information.

CS 4100Q
Decorative Quartz Epoxy Flooring System

Test Data

PROPERTIES	TYPICAL RESULTS	TEST METHOD
Compressive Strength	11,500 psi	ASTM C-579
Tensile Strength	2,500 psi	ASTM C-307
Flexural Strength	4,500 psi	ASTM C-580
Bond Strength to Concrete	415 psi (100% concrete failure)	ASTM D-4541
Flammability	Self Extinguishing	ASTM D-635
Heat Resistance Limitation	150° F to 200° F	
Hardness	80-85	ASTM D-2240 Shore D
Indentation	0.010 no chipping, cracking or delamination	MIL D-24613
Flexural Modulus of Elasticity	4.75X10 ⁵ psi	ASTM C-580
Tensile Elongation	7.5%	ASTM D-638
Coefficient of Friction	.90 Standard Texture .80 Medium Texture .70 Smooth Texture	ASTM D-2047
Impact Resistance	0.009 no chipping or delamination	MIL D-3134
Abrasion Resistance,	30-40 mg loss; CS-17 Wheel, 1,000 cycles	ASTM D-4060
Thermal Coefficient of Linear Expansion	1.8x10 ⁻⁵ in/in/°C	ASTM C-531
Water Absorption	0.02%	ASTM C-413



'USGBC' and related logo is a trademark owned by the U.S. Green Building Council and is used by permission.